



Adinath


Create, Enhance & Sustain

CC-499K : LEADED TIN BRONZE

Specification Sheet

DESCRIPTION

CC499K a Copper-Tin-Lead alloy exhibits good corrosion resistance in saline water and is insensitive to stress corrosion cracking.



CHEMICAL COMPOSITION

Element	Cu	Al	Fe	Ni	Zn	Pb	Sn	Si	S	Sb	P	Cd
Min (%)	84.00	-	-	-	4.00	-	4.00	-	-	-	-	-
Max (%)	88.00	0.01	0.30	0.60	6.00	3.00	6.00	0.01	0.04	0.10	0.04	0.02

Note : Ni includes Co; Cu+ named elements >= 99.5%; Unless otherwise noted, single values represent maximums.

COMPARATIVE SPECIFICATIONS

CuSn5Zn5Pb2

PACKING

ADINATH manufactures wide range of copper Alloys in the form of **Certified Ingots** weighing from 8-10 kgs each.

Standard Packaging of **1 Metric Ton** in Wooden Pallet.



CC-499K LEADED TIN BRONZE

VALUE ADDED SERVICES

Casting Range



25 Grams to 10 Kgs

Forging Sizes



50 Grams to 6 Kgs

Machining Sizes



1 mm to 200 mm

CONNECT WITH US Adinath Extrusion Pvt. Ltd.

Plot No. 4051-4055,
Bhagwan Mahavir Swami Marg,
G.I.D.C., Phase-III, Dared,
Jamnagar - 361004, Gujarat, India.

+91 7600 55 9243 +91 288 2730868
sales@adinathextrusion.com,
marketing@adinathextrusion.com
www.adinathextrusion.com

